

Technical Data Sheet

5663271

Data points have been determined using the ESTL Test method certified under ISO 17025: General requirements for the competence of testing and calibration laboratories.

Film Thickness			70 Gauge 17.7 Micron
FILM PROPERTIES	UNIT	NOMINAL UNIT	TOLERANCE
Ultimate @ Break	%	360	+/- 10%
Ultimate Force @ Break	Lbf	36	+/- 10%
Load Containment @ 300s	Lbf	4.3	+/- 10%
Elmendorf Tear Strength Force	Lbf	20.5	+/- 10%
Time to Break @ Tear	Sec	10	+/- 10%
Drop Time @ Tear	Sec	0.9	+/- 10%
Puncture Force	Lbf	4.8	+/- 10%
Displacement @ Puncture	Inch	2.6	+/- 10%
Peel Cling Force @ 300%	Lbf	0.65	+/- 10%

NOTE: The data presented above are nominal values of the product type described and must not be constructed as specifications. Therefore, no guarantee expressed or implied.